



*Stars Management DMCC*

---

# SUBMITTAL

## TRUE GRIP COATINGS

- ❖ AIM #1 (Base Coat)
  - ❖ WEARCOAT 66 (Top Coat)
  - ❖ SOFTSAND RUBBER (Aggregate)
-

TM

# AIM #1

## Urethane Industrial Membrane



**DESCRIPTION**

AIM #1 is a liquid applied urethane coating that forms a very tough, high performance barrier. It is used as a coating to protect and waterproof concrete gullies, docks and marinas, tile and concrete pipes, chemical safety dikes and wash-out basins. AIM #1 cures to a rubber-like finish that possesses excellent elasticity and will resist attack from the environment and from exposure to a wide variety of industrial chemicals.

**OUTSTANDING FEATURES**

- Forms a continuous membrane that resists penetration of a wide variety of chemicals
- Rapidly develops a high tensile strength and good elongation properties
- May be used on vertical, pitched, and horizontal surfaces
- Allows for movement of the substrate while maintaining excellent toughness
- Performs equally well as a coating, buried membrane, or below grade waterproofer
- Cures quickly; easy to apply

**APPLICATION**

Caution! Read this entire product data sheet before continuing.

All surfaces to be treated must be

clean, dry and free of all loose debris, oil, grease, and any other substance that would interfere with proper bond. A careful inspection of the surface should be made to detect any signs of damage or defects, and all repairs should be completed before application may proceed. Once preparation is completed, AIM #1 may be applied straight from the container after 3 minutes of low speed mechanical stirring. AIM #1 may be applied using a brush, roller, or airless spray technique at a wet film thickness of 30 mils. Andek recommends, in areas where reinforcement fabric is required, that Roofab (a specialty polyester fabric) be used. The fabric should be encapsulated between 2 coats of AIM #1 at a rate of 3-4 gallons per 100 square feet overall. Equipment may be cleaned after use with xylene or toluene before AIM #1 begins to dry.

**MAINTENANCE**

Repair any damaged areas by following the instructions in the application section of this data sheet.

**LIMITATIONS**

Protect AIM #1 from direct sunlight. This product is a moisture curing urethane and is packaged in specially sealed air-tight containers. If damaged, air and moisture may enter the container and cause premature curing. Cure time is 24 hours at 70°F (70% R.H.)

**PRECAUTIONS**

Warning! This product is combustible. Avoid sparks and open flames. Use only in well ventilated areas. Contains solvent and reactive isocyanate groups. Do not get in eyes or on skin or clothing. Wear chemical splash goggles, coveralls and rubber gloves when handling this

| SPECIFICATIONS        |                                |
|-----------------------|--------------------------------|
| Coating Type          | Moisture-cure urethane         |
| VOC                   | 100 gms/liter                  |
| Pot Life              | Single Component               |
| Shelf Life            | 2 years                        |
| Recommended Thickness | 40 mils dry film thickness     |
| Coverage              | 30 to 40 square feet/gallon    |
| Packaging             | 5 U.S. gallons (standard size) |
| Color                 | Black                          |

# AIM #1<sup>TM</sup>

## Urethane Industrial Membrane



product. Inhalation should be avoided. Persons with known respiratory allergies should avoid exposure to this product. For contact with skin or eyes, flush with clear water for 15 minutes. In case of inhalation, or in the event of eye contact, seek immediate medical attention.

**Keep out of reach of children and pets.**

For additional information, contact Andek's Technical Department.

| TECHNICAL DATA              |                                  |             |
|-----------------------------|----------------------------------|-------------|
| Moisture Vapor Transmission | 8.4 gms/M <sup>2</sup> /24 hours | ASTM E-96   |
| Flashpoint                  | 105°F                            | Seta        |
| Solids Content              | 90% (B.W.); 93% (B.V.)           | ASTM D-1044 |
| Softening Point (R&B)       | 240°F                            | ASTM D-903  |
| Viscosity at 70°F           | 7,000 cps                        | ASTM D-903  |
| Puncture Resistance         | 34 psi                           | FTMS 101B   |
| Impact Resistance           | 4mm indent                       | BS3900 (E3) |
| Tear Strength (minimum)     | 17 psi                           | ASTM D-624  |
| Tear Strength (maximum)     | 26 psi                           | ASTM D-624  |

*NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.*



**MATERIAL SAFETY DATA SHEET**  
**U.S. Department of Labor**  
**Occupational Safety & Health Administration**

**AIM #1**

**SECTION 1 – IDENTIFIERS**

MANUFACTURER: Andek Corporation  
TRADE NAME: AIM #1  
CHEMICAL FAMILY: Urethane Prepolymer Solution

**SECTION 2 – HAZARD IDENTIFICATION & EMERGENCY OVERVIEW**

**EMERGENCY OVERVIEW:** Toxic gases may be given off during burning or thermal decomposition. Closed container may forcibly rupture under extreme heat or when contents have been contaminated with water.

**EFFECTS OF OVEREXPOSURE:**

SKIN: Liquid may irritate skin.  
EYES: Contact may cause severe damage; vapor may irritate.  
BREATHING: Inhalation may cause headache, dizziness, nausea and irritation of respiratory tract.  
SWALLOWING: May be harmful or fatal if swallowed.

**SECTION 3 – COMPOSITION**

| <u>COMPONENT</u>  | <u>CAS #</u> | <u>APPROX %</u> | <u>TLV</u> |
|---|--------------|-----------------|------------|
| Iron Oxide  | 1309-37-1    | 16.2            |            |
| Barium Sulfate  | 7727-43-7    | 13.8            |            |
| Naphtha, Light Aromatic Solvent   | 64742-95-6   | 10.0            |            |
| Chlorinated Paraffin  | 8002-74-2    | 16.2            |            |
| Methylene Bisphenyl Isocyanate  | 101-68-8     | 2.8             |            |
| Polyether Prepolymer (Isocyanate Solution) boiling point <300°C; flash point >23°C) | N.O.S.       | 31.5            |            |
| Aromatic Hydrocarbon Resin  | 64742-90-1   | 9.5             |            |

KNOWN CARCINOGENS OR MUTAGENS - TYPE & DEFINITION – None known.

**SECTION 4 – FIRST AID MEASURES**

SKIN: Clean thoroughly with waterless hand cleaner, then follow with soap and water.  
EYES: Flush with water for 15 minutes and seek immediate medical attention.  
BREATHING: Move victim to fresh air. If asthmatic conditions occur, call a physician.  
SWALLOWING: Do NOT induce vomiting. Seek immediate medical attention.

**SECTION 5 – FIRE & EXPLOSION HAZARD DATA**

FLASH POINT (METHOD USED): 108°F. Closed Cup (ASTM D50).  
FLAMMABLE LIMITS: Lel 0.9; Uel 6.0.  
EXTINGUISHING MEDIA: Carbon dioxide; dry chemical; foam.  
SPECIAL FIRE FIGHTING PROCEDURES: If excessive fumes or smoke is encountered, wear self-contained respiratory equipment and full protective clothing.  
UNUSUAL FIRE & EXPLOSION HAZARDS: Sealed containers may build up pressure if exposed to heat (fire). Water can be used to cool the exterior of the containers.  
DECOMPOSITION PRODUCTS: Oxides of carbon, nitrogen, aluminum, possible HCN, polyurethane combustion compounds and halogens

**SECTION 6 – SPILL OR LEAK PROCEDURES**

**STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED:**  
Cover with a layer of sand or other suitable absorbent. Use protective measures as outlined under Section 8 below. Avoid contact with eyes, skin or clothing.

**SECTION 7 – HANDLING & STORAGE**

Avoid contact with moisture. Isocyanates react with water and generate CO<sup>2</sup> which may rupture sealed containers. Store between 40° and 80°F.

**SECTION 8 – PERSONAL PROTECTION/EXPOSURE CONTROLS**

RESPIRATORY PROTECTION (SPECIFY TYPE): In confined spaces use fresh air hood or NIOSH certified organic vapor canister unit. If used outdoors, ventilate well using a general or local exhaust ventilation.

EYE PROTECTION: Wear chemical splash goggles or face shield. Do not wear contact lenses while working with this material.

SKIN PROTECTION: Nitrile rubber gloves and apply a solvent-resistant barrier cream to areas of skin that may come in contact with this materials

OTHER PROTECTIVE EQUIPMENT: Eye wash station or fresh running water should be readily available. Wear coveralls and/or rubber apron and rubber shoes or boots.

PERSONAL HYGIENE: Wash hands thoroughly after handling and especially before eating or smoking. Shower at the end of the work shift. Wash contaminated clothing before reuse.

**SECTION 9 – PHYSICAL DATA**

|                       |           |                                       |         |
|-----------------------|-----------|---------------------------------------|---------|
| BOILING POINT (F)     | 312°      | SPECIFIC GRAVITY (H <sub>2</sub> O=1) | 1.2     |
| VAPOR PRESSURE        | 10        | PERCENT, VOLATILE BY VOLUME           | 18.0    |
| VAPOR DENSITY (AIR=1) | <4.8      | EVAPORATION RATE (N.B.A.=1)           | 0.2     |
| SOLUBILITY IN WATER   | Insoluble | pH (5% SLURRY)                        | Neutral |

APPEARANCE & ODOR - Black liquid with aromatic solvent odor.

**SECTION 10 – REACTIVITY DATA**

STABILITY: Stable.

INCOMPATABILITY (MATERIALS TO AVOID): Water (moisture); alcohols; amines; strong acids and bases.

HAZARDOUS DECOMPOSITION PRODUCTS: Possible HCN.

HAZARDOUS POLYMERIZATION: Will not occur.

CONDITIONS TO AVOID: Contamination with water will evolve CO<sup>2</sup>.

**SECTION 11 TOXICOLOGICAL INFORMATION**

|                           |                  |
|---------------------------|------------------|
| ACUTE ORAL TOXICITY       | Moderate         |
| ACUTE INHALATION TOXICITY | Moderate         |
| ACUTE DERMAL TOXICITY     | Slight           |
| SENSITIZATION             | Possible         |
| MUTAGENICTIY              | Negative         |
| CARCINOGENICITY           | Not Classifiable |

**SECTION 12 ECOLOGICAL INFORMATION**

|                                    |                  |
|------------------------------------|------------------|
| BIODEGRADATION                     | Slow To Moderate |
| TOXICITY TO FISH                   | Minimal          |
| TOXICITY TO AQUATIC INVERTEBRATES  | Minimal          |
| TOXICITY TO MICRO ORGANISMS        | Minimal          |
| ATMOSPHERIC OXIDATION OF VOLATILES | Degrades Rapidly |
| BIOACCUMULATION                    | Negative         |
| TOXICITY TO PLANTS                 | Minimal          |

**SECTION 13 – DISPOSAL CONSIDERATIONS**

Dispose of in accordance with existing federal, state, and local environmental laws.

**SECTION 14 – TRANSPORT INFORMATION**

|                       |         |
|-----------------------|---------|
| PROPER SHIPPING NAME: | Paint   |
| HAZARD CLASS:         | 3       |
| PACKING GROUP:        | III     |
| ID #:                 | UN 1263 |
| RQ:                   | None    |

TRANSPORT LABELS REQUIRED: Flammable liquid. (In the U.S., this material may be re-classified as a combustible liquid and is not regulated in containers less than 119 gallons via surface transportation.)

**SECTION 15 – REGULATORY INFORMATION**

See reference data for individual components



**MATERIAL SAFETY DATA SHEET**  
**U.S. Department of Labor**  
**Occupational Safety & Health Administration**

**AIM #1**

**SECTION 16 – OTHER INFORMATION (HMIS RATING)**

|                     |   |
|---------------------|---|
| Health              | 2 |
| Flammability        | 2 |
| Physical Hazard     | 1 |
| Personal Protection | H |

---

**Disclaimer:** Andek Corporation (Andek) believes, to the best of its knowledge, information and belief, the information contained herein to be accurate and reliable as of the issue date of this Material Safety Data Sheet (MSDS). However, because the conditions of handling, use, and storage of these materials are beyond Andek's control, we assume no responsibility or liability for personal injury or property damage incurred by the use of these materials and make no warranty, expressed or implied, regarding the accuracy or reliability of the data or results obtained from their use. All materials may present unknown hazards and should be used with caution. The information and recommendations contained in this MSDS are offered for the users' consideration and examination. It is the responsibility of the user to determine the final suitability of this information and data and to comply with all applicable international, federal, state, and local laws and regulations.

---

# WEARCOAT 66<sup>TM</sup>

Traction Enhancing Coating



## DESCRIPTION

WEARCOAT 66 is a solvent based cyclo-aliphatic urethane based coating. It produces a tough, glossy, hard-wearing and chemically resistant surface for the protection of urethane and polyester composites, concrete, masonry, and over approved substrates. WEARCOAT 66 is available as a transparent, glossy coating or as a pigmented material that possesses excellent color fastness and ultra-violet radiation resistance as well as high tensile strength. WEARCOAT 66 will encapsulate most aggregates, including sharp, angular types used for traction enhancement.

## OUTSTANDING FEATURES

- ✓ Available in a wide variety of colors and textures
- ✓ Will encapsulate rough, angular aggregates
- ✓ Cured film is flexible, tough, and abrasion-resistant
- ✓ May be used for traction enhancement in pedestrian and vehicular situations
- ✓ Accommodates normal substrate movement and thermal stresses
- ✓ Highly resistant to staining and deterioration from most chemicals
- ✓ Maintains its attractive, clean appearance
- ✓ Easily scrubbed and cleaned to maintain its attractive, clean appearance

## APPLICATION

Caution! Read this entire data sheet before continuing.

All surfaces to be coated must be clean, dry, and completely free of loose particles, oil, grease, or any substance that would interfere with proper bond. WEARCOAT 66 may be applied over products such as Polafloor Epoxy High Build at any time after the surface has been thoroughly set for at least 1 hour. If overcoating a painted surface, check compatibility first, as some paints may bleed color or be lifted by solvents.

Add Part 'B' color concentrate to the clear Part 'A' and stir thoroughly for 3 minutes. WEARCOAT 66 is applied at a rate of 400 square feet per gallon per coat.

WEARCOAT 66 may be applied

by brush, roller, or airless spray technique in a thin, even coat. If traction enhancement is required, iron-free sharp white quartz sand or any approved aggregate may be broadcast into the wet WEARCOAT 66. After the first coat has thoroughly dried with the embedded aggregate, a second coat of WEARCOAT 66 is applied to thoroughly encapsulate the aggregate. Sized and graded sharp white quartz sand and coarse Estes aggregate are available from Andek Corporation. Equipment may be cleaned with toluene or xylene while the WEARCOAT 66 is still wet.

## MAINTENANCE

To repair damaged areas, coarse sanding should be followed by thorough cleaning with fresh water. WEARCOAT 66 may then be re-applied to the

| SPECIFICATIONS        |   |
|-----------------------|---|
| Coating Type          | Two-part aliphatic urethane                   |
| VOC                   | 320 gms/liter                                 |
| Pot Life              | 3 hours @ 70°F (50% R.H.)                     |
| Shelf Life            | 12 months                                     |
| Recommended Thickness | 3 mils dry film thickness per coat            |
| Coverage              | 2 coats @ 400 square feet per gallon per coat |
| Packaging             | 1 gallon or 5 gallon units                    |
| Color                 | A variety of standard and custom colors       |

# WEARCOAT 66

Traction Enhancing Coating



clean, dry surface.

**LIMITATIONS**

Store in a cool, dry place away from direct sunlight. Avoid opened containers, as moisture will cure the material. Do not apply in temperatures below 35° F. Application must be protected from precipitation for at

least 4 hours. Shelf life is 12 months when stored in proprietary sealed containers between 45°F and 85°F.

**PRECAUTIONS**

During handling of this product, it is recommended that standard of ingestion, do NOT induce safety equipment such as rubber vomiting and seek immediate gloves, chemical splash goggles medical attention.

and coveralls be worn. Avoid contact with skin and eyes. In case of contact, flush with clear water for 15 minutes. In case of eye contact, get immediate medical attention in addition to flushing. Do not ingest. In case Of ingestion, do NOT induce Vomiting and seek immediate Medical attention.

| TECHNICAL DATA                 |                            |                   |
|--------------------------------|----------------------------|-------------------|
| Resistance to Corrosion        | 10                         | ASTM D-1654       |
| Shore 'A' Hardness             | 95                         | ASTM D-2240       |
| Tensile Strength               | 4,500 lb/square inch       | ASTM D-412        |
| Elongation                     | 10%                        | ASTM D-412        |
| Solids Content                 | 48% (B.W.); 44% (B.V.)     | ASTM D-1044       |
| Flashpoint                     | 110°                       | FTMS 141A (M4293) |
| Flexibility @ Low Temperatures | 180 deg. Bend @ 20°F       | ASTM C-711        |
| Impact Resistance              | 4mm indent                 | ASTM D-1474       |
| Water Absorption               | Zero                       | ASTM D570-77      |
| Working Time                   | 3 hours @ 70°F (50% R.H.)  |                   |
| Drying Time                    | 1½ hours @ 70°F (50% R.H.) |                   |
| Cure Time                      | 24 hours @ 70°F            |                   |
| Weatherometer (5000 hours)     | Pass                       | ASTM G-23         |

NOTICE: The information presented herein is based on tests and data that Andek Corporation believes to be reliable. It is intended for use by technically qualified personnel at their own discretion and risk. Since conditions of handling and use are beyond our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. Nothing herein is to be construed as a license to operate or a recommendation to infringe any patent.





**MATERIAL SAFETY DATA SHEET**  
**U.S. Department of Labor**  
**Occupational Safety & Health Administration**

**WEARCOAT 66 – PART A**

**SECTION 1 - IDENTIFIERS**

MANUFACTURER: Andek Corporation  
TRADE NAME: Wearcoat 66 Part A  
CHEMICAL FAMILY: Urethane Prepolymer Solution

**SECTION 2 – HAZARD IDENTIFICATION & EMERGENCY OVERVIEW**

Emergency Overview: Toxic gases may be given off during burning or thermal decomposition. Closed container may forcibly rupture under extreme heat or when contents have been contaminated with water.

**Effects of Overexposure:**

SKIN: May cause dermal sensitization. May be absorbed through skin.  
EYES: Contact may cause severe damage. Vapor may irritate.  
BREATHING: Inhalation may cause headache, dizziness, nausea and irritation. Inhalation of spray mist may be toxic.  
SWALLOWING: Harmful or fatal if swallowed.

**SECTION 3 - COMPOSITION**

| <u>COMPONENT</u>                     | <u>CAS #</u> | <u>APPROX %</u> | <u>TLV</u>    |
|--------------------------------------|--------------|-----------------|---------------|
| Isophorone Di-isocyanate Homopolymer | 53880-05-0   | 65.0            | N/A           |
| Naphtha, Light Aromatic Solvent      | 64742-95-6   | 20.0            | N/A           |
| Methyl Amyl Ketone                   | 110-43-0     | 14.0            | 50.0ppm TWA   |
| Isophorone Di-isocyanate             | 4098-71-9    | <1.0            | 0.005 ppm TWA |

**SECTION 4 – FIRST AID MEASURES**

SKIN: Clean thoroughly with waterless hand cleaner, followed with soap and water.  
EYES: Flush with clear water for 15 minutes and seek immediate medical attention.  
BREATHING: Move victim to fresh air and give artificial respiration or oxygen if needed.  
SWALLOWING: DO NOT induce vomiting. Seek immediate medical attention.

**SECTION 5 – FIRE & EXPLOSION HAZARD DATA**

FLASH POINT (METHOD USED): 97°F. Closed Cup (ASTM D50).  
FLAMMABLE LIMITS: Lel 0.9; Uel 6.0.  
EXTINGUISHING MEDIA: Carbon dioxide; dry chemical; foam.  
SPECIAL FIRE FIGHTING PROCEDURES: If excessive fumes or smoke is encountered, wear self-contained breathing apparatus and full protective equipment.  
UNUSUAL FIRE & EXPLOSION HAZARDS: Sealed containers may build up pressure if exposed to heat (fire). Water can be used to cool the exterior of the containers.  
DECOMPOSITION PRODUCTS: Oxides of carbon and nitrogen, possible HCN and polyurethane combustion compounds.

**SECTION 6 – SPILL OR LEAK PROCEDURES**

Cover with a layer of sand or other suitable absorbent. Use protective measures as outlined in Section 8 below. Avoid contact with skin, eyes and clothing.

**SECTION 7 – HANDLING & STORAGE**

CAUTION: Flammable liquid. Keep away from all sources of ignition. Use with adequate ventilation. Avoid prolonged or repeated contact with skin. Avoid contact with moisture.

**SECTION 8 – PERSONAL PROTECTION/EXPOSURE CONTROLS**

RESPIRATORY PROTECTION (SPECIFY TYPE): In confined spaces use fresh air hood or NIOSH certified organic vapor canister unit. If used indoors, ventilate well using a general or local exhaust ventilation. Ref: OSHA's respirator regulations in 29CFR 1910.134.  
EYE PROTECTION: Wear chemical splash goggles or face shield. Do not wear contact lenses while working with this material. Ref: OSHA's eye and face protections in 29CFR 1910.133.  
SKIN PROTECTION: Nitrile rubber gloves to prevent skin contact.

OTHER PROTECTIVE EQUIPMENT: Coveralls and/or apron, rubber shoes or boots, eye wash station or fresh running water should be readily available.

PERSONAL HYGIENE: Wash hands thoroughly after handling and especially before eating or smoking. Shower at the end of work shift. Wash contaminated clothing before reuse.

**SECTION 9 - PHYSICAL DATA**

|                       |           |                                       |         |
|-----------------------|-----------|---------------------------------------|---------|
| BOILING POINT (F)     | 312°      | SPECIFIC GRAVITY (H <sub>2</sub> O=1) | 0.92    |
| VAPOR PRESSURE        | 10        | PERCENT, VOLATILE BY VOLUME           | 34%     |
| VAPOR DENSITY (AIR=1) | 4.8       | EVAPORATION RATE (N.B.A.=1)           | 0.25    |
| SOLUBILITY IN WATER   | Insoluble | pH (5% SLURRY)                        | Neutral |

APPEARANCE & ODOR - Clear liquid with sweet, perfume-like odor.

**SECTION 10 – REACTIVITY DATA**

STABILITY: Stable.

INCOMPATIBILITY (MATERIALS TO AVOID): Water (moisture); alcohols; amines; strong acids and bases.

HAZARDOUS DECOMPOSITION PRODUCTS: Oxides of carbon and nitrogen, possible HCN and polyurethane combustion compounds.

HAZARDOUS POLYMERIZATION: Will not occur.

CONDITIONS TO AVOID: Excessive heat and/or wet conditions.

**SECTION 11 TOXICOLOGICAL INFORMATION**

|                           |                  |
|---------------------------|------------------|
| ACUTE ORAL TOXICITY       | MODERATE         |
| ACUTE INHALATION TOXICITY | SERIOUS          |
| ACUTE DERMAL TOXICITY     | MODERATE         |
| SENSITIZATION             | POSSIBLE         |
| MUTAGENICTY               | NEGATIVE         |
| CARCINOGENICITY           | NOT CLASSIFIABLE |

**SECTION 12 ECOLOGICAL INFORMATION**

|                                    |                 |
|------------------------------------|-----------------|
| BIODEGRADATION                     | SLOW            |
| TOXICITY TO FISH                   | SLIGHT          |
| TOXICITY TO AQUATIC INVERTEBRATES  | SLIGHT          |
| TOXICITY TO MICRO ORGANISMS        | SLIGHT          |
| ATMOSPHERIC OXIDATION OF VOLATILES | DEGRADE RAPIDLY |
| BIOACCUMULATION                    | MINIMAL         |
| TOXICITY TO PLANTS                 | SLIGHT          |

**SECTION 13 – DISPOSAL CONSIDERATIONS**

Dispose of in accordance with local, state and federal regulations.

**SECTION 14 – TRANSPORT INFORMATION**

|                            |                   |
|----------------------------|-------------------|
| PROPER SHIPPING NAME:      | Paint             |
| HAZARD CLASS:              | 3                 |
| PACKING GROUP:             | III               |
| ID #:                      | UN 1263           |
| RQ:                        | None              |
| TRANSPORT LABELS REQUIRED: | Flammable liquid. |

**SECTION 15 – REGULATORY INFORMATION**

See reference data for individual components.

**SECTION 16 – OTHER INFORMATION (HMIS RATING)**

|                     |   |
|---------------------|---|
| Health              | 3 |
| Flammability        | 2 |
| Physical Hazard     | 1 |
| Personal Protection | H |







---

Disclaimer: Andek Corporation (Andek) believes, to the best of its knowledge, information and belief, the information contained herein to be accurate and reliable as of the issue date of this Material Safety Data Sheet (MSDS). However, because the conditions of handling, use, and storage of these materials are beyond Andek's control, we assume no responsibility or liability for personal injury or property damage incurred by the use of these materials and make no warranty, expressed or implied, regarding the accuracy or reliability of the data or results obtained from their use. All materials may present unknown hazards and should be used with caution. The information and recommendations contained in this MSDS are offered for the users' consideration and examination. It is the responsibility of the user to determine the final suitability of this information and data and to comply with all applicable international, federal, state, and local laws and regulations.

---



## PROJECT REFERENCES

|  | PROJECT                                    | LOCATION                                   | ANDEK PRODUCT USED        |
|--|--|--|---------------------------|
|    | U.S. Naval Research Lab                    | Washington DC                              | Polaroof NW               |
|    | Reagan National Control Tower              | Reagan National Airport,<br>Washington, DC | Polaroof AC, Wearcoat 66  |
|   | Arch Street Presbyterian Church            | Philadelphia, PA                           | Polaprime 21, Polaroof AC |
|  | Trump Building Wall Street<br>(Metal roof) | New York, NY                               | Polaprime 21, Polaroof AC |
|  | PA DOT-Interstate 476                      | Pennsylvania                               | Polagard AG               |
|  | McDonnell Douglas (Boeing<br>Aerospace)    | New Jersey                                 | Polaroof RAC              |



John F Kennedy Airport

New York, NY

Polaroof SP, Flashband



LaGuardia Airport

New York, NY

Polaroof SP, Flashband



Throgs Neck Bridge

New York, NY

Roofdx Super, Roofab



Los Angeles Int'l Airport

Los Angeles, CA

Polaroof RAC, Roofab, Polaroof SP



PSE&G Nuclear Power Station

Salem, NJ

Andek 950, Wearcoat 66



Philadelphia Park Horse Stables

Philadelphia, PA

Polaprime 21, Polaroof AC



U.S. Air Force Airlift Command

Dover AFB, DE

Polaroof AC



U.S. Navy (Military Sealift  
Command)

Norfolk, VA

Polaroof SP



Walt Disney World

Orlando, FL

Roofdx Super, Polarroof RAC, Roofab, Polarroof AC, Polarroof NW, Clearcoat 44



The Moshulu

Philadelphia, PA

Polaprime 21, Roofab, Polarroof RAC



Interstate 78

Pennsylvania

Polagard AG



Veteran's Administration Hospitals

Delaware & Palo Alto, CA

Polarroof RAC, Polarroof SP



Jazzland Amusement Park

New Orleans, LA

Polagard AG



NASA Goddard Space Flight Center

Greenbelt, MD

Polarroof RAC, Roofab



National Institutes of Health

Bethesda, MD

Cocoon 560, Cocoon Vinyl Bond B



Harrah's Casino

Atlantic City, NJ

Polaroof AC, Roofdx Copper



General Electric

Burkeville, AL

Cocoon 560, Cocoon Vinyl Bond B



Baltimore/Washington Int'l Airport

BWI Airport, MD

Polaroof NW



U.S. Department of State

Overseas Embassies

Rubberkote 1047



Princeton University

Princeton, NJ

Polaroof AC, Polaroof NW,  
Wearcoat 44, Roofab



U.S. Army Corps of Engineers

Hungry Horse, MT &  
Johnson Atoll

Polajoint



Dupont Corp

Richmond, VA

Polafloor PUR, Wearcoat 44,  
Polafloor Epoxy Topping



Lucy the Elephant

Margate, NJ

Polaroof AC, Polaprime 21



Maryland DOT

Chesapeake House  
Service Center

Polaroof AC, AIM #3



Philadelphia City Hall

Philadelphia, PA

Roofdx Super



Pfizer Pharmaceutical

Philadelphia, PA

Polafloor PUR



Philadelphia Naval Shipyard

Philadelphia, PA

Polaroof AC, Polaroof NW,  
Wearcoat 44, Roofab



University of Texas

Austin, TX

Clearcoat 44



Delaware DOT

Harrington, DE

Polaroof NW



The Ritz Carlton Resort & Golf  
Club

Bradenton, FL

Andek Firegard



Pennsylvania State University  
Wiley Lab

State Park, PA

Cocoon 560, Cocoon Vinyl Bond B



Hershey Park

Hershey, PA

Polafloor Colorcoat





National Italian Foundation HQ

Washington D.C.

Polagard Fibrelastic



Independence Blue Cross/Blue Shield HQ

Philadelphia, PA

Roofdx Super, Polafloor PUR



U.S. Navy - Military Sealift Command

Norfolk, VA


Polaroof SP

**Picatinny**

U.S. Army

Picatinny Arsenal, NJ

Polajoint Super



Noramco Pharmaceuticals

Wilmington, DE

Polaprime 21, Polaroof NW, Clearcoat 44



U.S. Coast Guard

Cape May, NJ

Polaroof SP, Polaroof RAC, Roofab



Bank of America

Baltimore, MD

Polaprime 21, Roofdx Super, Polaroof RAC, Roofab



Blue Cross/ Blue Shield

Columbia, SC

Polagard AG





Osiris Therapeutics

Columbia, MD

Cocoon 560, Cocoon Vinyl Bond B



Delaware "Smoke House" Fire  
Training Facility

Polaprime 21, Wearcoat 44



Kentucky Horse Park-Central  
Show Arena Facility

Lexington, KY

Polaprime 21, Polarof NW



Triborough Bridge & Tunnel  
Authority

New York, NY

Roofdx Super, Roofab, Silver Film



Druid Hill Recreation Center

Baltimore, MD

Wearcoat 44